

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

Datasheet AE1400PBT



AE1400PBT is an internally lubricated material which shows a significantly reduced coefficient of friction and increased resistance to wear compared to unfilled PET. It even outperforms materials such as wax of oil filled Cast Nylon products. It's also a material of choice for applications involving soft metal and plastic mating surface.

Application

Rollers, precision plain bearings, toothed gears, valves, distribution valves, etc.

Material

Thermoplastic Polyester + solid lubricant.

Availablity

	Value	Unit
Rod diameters	6-140	mm
Tube inside diameter	10-160	mm
Tube outside diameter	25-210	mm
Length standard	3000	mm
Sheet thickness	8-100	mm
Sheet size	610×2000	mm





The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.



ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

AE1400PBT - Specifications

Physical properties

	Test standard	Value	Unit
Density		1,39	g/cm³
Thermal conductivity		on request	
Specific heat capacity		on request	
Moisture absorption at 23°C, 50% RH	ISO 62	0,23	%
Water absorption at 23 °C	ISO 62	0,5	%
Flammability	UL 94	НВ	[-]

Mechanical properties

· · · · · · · · · · · · · · · · · · ·				
	Test standard	Value	Unit	
Tensile strength	ISO 527	80	MPa	
Hardness	ISO 868	81	SHORE-D	
Yield stress	ISO 527	80	MPa	
Elongation at break	ISO 527	10	%	
Modulus of elasticity in tension	ISO 527	3300	MPa	
Bending modulus	Flexural test	3000	MPa	
Flexural strength	ISO 178	115	MPa	
Charpy impact strength +23°C	ISO 179/1eU	60	kJ/m²	
Charpy notched impact strength +23°C	ISO/1eA	2,8	kJ/m²	
Ball indentation hardness	ISO 2039-1	175	MPa	
Compressive modulus	ISO 604	2800	MPa	

Thermal properties

	Test standard	Value	Unit
Min. working temperature		-20	°C
Max. working temperature		110	°C
Intermittent working temperature		160	°C
Heat distortion temperature	Method A ISO 75	100	°C
Melting temperature		on request	
Thermal coefficient of linear expansion	DIN 53752	6	1/K.10-5

Friction properties

Test standard	Value	Unit

Electrical properties

	Test standard	Value	Unit
Dielectric constant		on request	
Dielectric loss factor		on request	
Dielectric strength	IEC 243	20	KV/mm
Dielectric constant at 1MHZ	IEC 250	3,3	[-]

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.

Electrical properties

Volume resistivity		on request		
Surface resistivity	IEC 93	10 ¹³	Ω	
Resistance to tracking (CTI)	DIN EN 60112	600	[-]	

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.