

Datasheet AIEPGC310



AI EP GC 310 Can be describe as an all-in-one material. The carefully composed resins combine with the glass base result not only in exceptional resistance, but also amazing electrotechnical properties. Suitable for countless applications.

Application

Electrical and mechanical application with flammability UL 94 V-0 with halogen-free flame protection V-0

Material

Epoxy with woven glass cloth composite

Availability

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	



AIEPGC310 - Specifications

Physical properties

	Test standard	Value	Unit
Density		1,9	g/cm ³
Water absorption at 23 °C		34	mg
Flammability		V-0	[-]

Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		300	MPa
Shear strength		30	MPa
Impact strength		on request	
Flexural strength		on request	
Insulation resistance		on request	
Elastic modulus from bending test		22000	MPa
Compressive strength perpendicular		350	MPa
Izod impact strength, parallel with layers		42	Kj/m ²
Shear strength parallel		on request	

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		130	T.I.

Friction properties

	Test standard	Value	Unit
--	---------------	-------	------

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		on request	
Resistance to tracking (CTI)		200	CTI
Permittivity 50Hz		5,5	[-]
Permittivity 1MHz		5,5	[-]
Dissipation factor 50Hz		0,04	[-]
Dissipation factor 1 MHz		0,04	[-]
Insulation resistance after submersion in water		50.000	MΩ