

## Datasheet AIPFCP205



AI PF CP 205 is a phenolic strengthened paper based composite material

### Application

### Material

Phenolic strengthened paper based composite

### Availability

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	



## AIPFCP205 - Specifications

### Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,35	g/cm <sup>3</sup>
Water absorption at 23 °C		113	mg
Flammability		V-1	[-]

### Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		60	MPa
Shear strength		20	Mpa
Impact strength		on request	
Flexural strength		75	MPa
Insulation resistance		on request	
Elastic modulus from bending test		5.000	MPa
Compressive strength perpendicular		250	MPa
Izod impact strength, parallel with layers		on request	
Shear strength parallel		on request	

### Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		100	T.I.

### Friction properties

	Test standard	Value	Unit
--	---------------	-------	------

### Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		8,4	kV/mm
Resistance to tracking (CTI)		100	CTI
Permittivity 50Hz		on request	
Permittivity 1MHz		5,5	[-]
Dissipation factor 50Hz		on request	
Dissipation factor 1 MHz		0,05	[-]
Insulation resistance after submersion in water		1.000	MΩ