

Datasheet AIPFCP207



AI PF CP 207 is a phenolic strengthened paper based composite material

Application

Material

Phenolic strengthened paper based composite

Availability

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	



AIPFCP207 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,35	g/cm ³
Water absorption at 23 °C		920	mg
Flammability		on request	

Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		100	MPa
Shear strength		10	Mpa
Impact strength		on request	
Flexural strength		80	MPa
Insulation resistance		on request	
Elastic modulus from bending test		5.000	MPa
Compressive strength perpendicular		300	MPa
Izod impact strength, parallel with layers		on request	
Shear strength parallel		on request	

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		105	T.I.

Friction properties

	Test standard	Value	Unit
--	---------------	-------	------

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		on request	
Resistance to tracking (CTI)		100	CTI
Permittivity 50Hz		on request	
Permittivity 1MHz		on request	
Dissipation factor 50Hz		on request	
Dissipation factor 1 MHz		on request	
Insulation resistance after submersion in water		on request	